

UMKA COLOR GD2

Technical Specification Technische Werte Tehnička Specifikacija

Grammage Gewicht Gramatura	Thickness Dicke Debljina	Stiffness / Steifigkeit / Krutost	
		LW5 ⁰	
		mNm	
g/m ²	mm	md / längs / ds	cd / quer/ps
230	0,285	9,3	4,0
250	0,315	13,5	5,7
280	0,360	19,6	8,1
300	0,390	24,2	10,1
320	0,415	30,7	12,3
350	0,450	39,7	15,9
400	0,525	59,6	22,9
450	0,590	77,9	30,0
500	0,675	97,8	37,6

Testing method / Meßmethode/ Metod testiranja	Tolerances / Toleranzen / Tolerancija	
Brightness / Weißgrad / Belina:	ISO 2470	80 ±1%
Grammage / Gewicht / Gramatura:	ISO 536	+/-2%
Thickness / Dicke / Debljina:	ISO 534	+/-5%
Stiffness / Steifigkeit / Krutost:	DIN 53121	-15%
Testing climate / Prüfklima / Uslovi testiranja:	23 (±1) ⁰ C 50(±2)% rh	

Recommended printing methods/ Die empfohlene Druckmethode/ Preporučeni metod štampanja:
Offset, Flexo./ Offset, Flexodruck /Ofset, flekso štampa.

Valid from 02/2007

Umka AD Beograd, 13. Oktobra 1,11260 Umka
Tel: +381 11 36 02 600, Fax: +381 11 8026 995
Email: sales@umka.rs <http://www.umka.rs>