



TECHNICAL DATA SHEET

Snowbulk 70 ISO / Bluish colour 4.0/ 53 gsm / bulk 2.0

Parameter	Value	Tolerance
Brightness	70%	-1/+0,5 %
Basis Weight	53 g/m ²	-2/+3 g/m ²
Bulk / Volume	2.0	
Caliper	106 micron	+/- 4 micron
Shade	4 (Standard bluish)	+/- 0.4
Opacity	92	+/- 1
Moisture	8-9%	+/- 0.5
Tear	240 to 300mN	
Tensile	2.40 to 3.00 kN/m	
Main furnish	85 to 90% mechanical groundwood	
Secondary furnish	10 to 15% Cellulose	
Wrapping	Kraft wrappers – 2 layers	
Cores	76mm strawboard – 152 mm on request	
Joins	Maximum 2 joins per reel, marked by red line	
Reel Diameter	1000mm or 1150mm	
Accreditation	FSC on request	Volume Credit

All paper supplied according to the *General Trade Rules for Sales of Paper and Paperboard*

Should Technical Data be required for a specific grammage / caliper combination these can be provided upon request.



TECHNICAL DATA SHEET

Snowbright 75 ISO / Creamy colour 9.0/ 55 gsm / bulk 2.0

Parameter	Value	Tolerance
Brightness	75%	-1/+0,5 %
Basis Weight	55 g/m ²	-2/+3 g/m ²
Bulk / Volume	2.0	
Caliper	110 micron	+/- 4 micron
Shade	9.0 (Standard creamy)	+/- 0.4
Opacity	87	+/- 1
Moisture	8-9%	+/- 0.5
Tear	240 to 300mN	
Tensile	2.40 to 3.00 kN/m	
Main furnish	85 to 90% mechanical groundwood	
Secondary furnish	10 to 15% Cellulose	
Wrapping	Kraft wrappers – 2 layers	
Cores	76mm strawboard – 152 mm on request	
Joins	Maximum 2 joins per reel, marked by red line	
Reel Diameter	1000mm or 1150mm	
Accreditation	FSC on request	Volume Credit

All paper supplied according to the *General Trade Rules for Sales of Paper and Paperboard*

Should Technical Data be required for a specific grammage / caliper combination these can be provided upon request.



TECHNICAL DATA SHEET

Snowbright 75 ISO / Creamy colour 9.0/ 70 gsm / bulk 2.0

Parameter	Value	Tolerance
Brightness	75%	-1/+0,5 %
Basis Weight	70 g/m ²	-2/+3 g/m ²
Bulk / Volume	2.0	
Caliper	140 micron	+/- 4 micron
Shade	9.0 (Standard creamy)	+/- 0.4
Opacity	90	+/- 1
Moisture	8-9%	+/- 0.5
Tear	240 to 300mN	
Tensile	2.40 to 3.00 kN/m	
Main furnish	85 to 90% mechanical groundwood	
Secondary furnish	10 to 15% Cellulose	
Wrapping	Kraft wrappers – 2 layers	
Cores	76mm strawboard – 152 mm on request	
Joins	Maximum 2 joins per reel, marked by red line	
Reel Diameter	1000mm or 1150mm	
Accreditation	FSC on request	Volume Credit

All paper supplied according to the *General Trade Rules for Sales of Paper and Paperboard*

Should Technical Data be required for a specific grammage / caliper combination these can be provided upon request.



TECHNICAL DATA SHEET

Snowbright 75 ISO / Creamy colour 9.0/ 80 gsm / bulk 2.0

Parameter	Value	Tolerance
Brightness	75%	-1/+0,5 %
Basis Weight	80 g/m ²	-2/+3 g/m ²
Bulk / Volume	2.0	
Caliper	160 micron	+/- 4 micron
Shade	9.0 (Standard creamy)	+/- 0.4
Opacity	92	+/- 1
Moisture	8-9%	+/- 0.5
Tear	240 to 300mN	
Tensile	2.40 to 3.00 kN/m	
Main furnish	85 to 90% mechanical groundwood	
Secondary furnish	10 to 15% Cellulose	
Wrapping	Kraft wrappers – 2 layers	
Cores	76mm strawboard – 152 mm on request	
Joins	Maximum 2 joins per reel, marked by red line	
Reel Diameter	1000mm or 1150mm	
Accreditation	FSC on request	Volume Credit

All paper supplied according to the *General Trade Rules for Sales of Paper and Paperboard*

Should Technical Data be required for a specific grammage / caliper combination these can be provided upon request.



TECHNICAL DATA SHEET

Super Snowbright 80 ISO / Bluish colour 1.0/ 55 gsm / bulk 2.0

Parameter	Value	Tolerance
Brightness	80%	-1/+0,5 %
Basis Weight	55 g/m ²	-2/+3 g/m ²
Bulk / Volume	2.0	
Caliper	110 micron	+/- 4 micron
Shade	1.0 (Bluish white)	+/- 0.4
Opacity	86	+/- 1
Moisture	8-9%	+/- 0.5
Tear	240 to 300mN	
Tensile	2.40 to 3.00 kN/m	
Main furnish	85 to 90% mechanical groundwood	
Secondary furnish	10 to 15% Cellulose	
Wrapping	Kraft wrappers – 2 layers	
Cores	76mm strawboard – 152 mm on request	
Joins	Maximum 2 joins per reel, marked by red line	
Reel Diameter	1000mm or 1150mm	
Accreditation	FSC on request	Volume Credit

All paper supplied according to the *General Trade Rules for Sales of Paper and Paperboard*

Should Technical Data be required for a specific grammage / caliper combination these can be provided upon request.



TECHNICAL DATA SHEET

Super Snowbright 80 ISO / Bluish colour 1.0/ 80 gsm / bulk 2.0

Parameter	Value	Tolerance
Brightness	80%	-1/+0,5 %
Basis Weight	80 g/m ²	-2/+3 g/m ²
Bulk / Volume	2.0	
Caliper	160 micron	+/- 4 micron
Shade	1.0 (Bluish white)	+/- 0.4
Opacity	93	+/- 1
Moisture	8-9%	+/- 0.5
Tear	240 to 300mN	
Tensile	2.40 to 3.00 kN/m	
Main furnish	85 to 90% mechanical groundwood	
Secondary furnish	10 to 15% Cellulose	
Wrapping	Kraft wrappers – 2 layers	
Cores	76mm strawboard – 152 mm on request	
Joins	Maximum 2 joins per reel, marked by red line	
Reel Diameter	1000mm or 1150mm	
Accreditation	FSC on request	Volume Credit

All paper supplied according to the *General Trade Rules for Sales of Paper and Paperboard*

Should Technical Data be required for a specific grammage / caliper combination these can be provided upon request.

Product Assortment (EMA & most popular used)

			Bulk					
Snowbulk	70 ISO	GSM	1,6	1,8	2,0	2,2	2,3	2,4
	Col. 7,5	50	N/A		•			•
		55	•	•				
		60		•	•		•	
		70	•	•		•		
		80				•	N/A	N/A
		90				N/A	N/A	N/A
Snowbulk	70 ISO	GSM	1,6	1,8	2,0	2,2	2,3	2,4
	Col. 4,0	53	N/A		EMA		•	
		55						
		60			•			
		70						
		80					N/A	N/A
		90				N/A	N/A	N/A
Snowbright	75 ISO	GSM	1,6	1,8	2,0	2,2	2,3	2,4
	Col. 9,0	50	N/A				•	
		55			EMA			
		60	•	•	•		•	
		70			EMA	•	•	
		80	•		EMA		N/A	N/A
		90		•	•	N/A	N/A	N/A
Snowbright	75 ISO	GSM	1,6	1,8	2,0	2,2	2,3	2,4
	Col. 4,0	50	N/A					
		55						
		60						
		70					•	
		80					N/A	N/A
		90				N/A	N/A	N/A
Super Snowbright	80 ISO	GSM	1,6	1,8	2,0	2,2	2,3	2,4
	Col. 1,0	55	N/A		EMA			
		60			•			
		70			•			
		80		•	EMA		N/A	N/A
		90				N/A	N/A	N/A
Super Snowbright	80 ISO	GSM	1,6	1,8	2,0	2,2	2,3	2,4
	Col. 8,0	60	•	•	•		•	
		70	•	•	•			

80	•	•	•		N/A	N/A
90	•	•	•	N/A	N/A	N/A

ALL OTHER QUALITIES ARE ALSO POSSIBLE FOR PRODUCTION, BUT SUBJECT TO
DIFFERENT MILL'S REQUIREMENTS