

GC2 Cream

Technical Information	Unit	Margins	Specs										
			200	215	220*	235	240*	250	270	295	325	350	380
Grammage	g/m ²	±5%	200	215	220*	235	240*	250	270	295	325	350	380
Thickness	µm	±5%	325	350	360	385	400	420	460	510	560	610	660
Bulk			1.63	1.63	1.64	1.64	1.66	1.68	1.70	1.73	1.72	1.74	1.74
Taber(15°)CD	mN•m	≥	2.7	4.6	5.2	6.8	7.2	8.1	10.0	13.0	16.0	20.0	24.0
Taber(15°)MD	mN•m	≥	6.0	9.4	10.4	13.5	14.5	16.5	20.2	26.3	32.5	36.0	42.5
Moisture	%	±1.0	7										
PPS Smoothness - Top	µm	≤	2										
Brightness - Top	%	±2.0	80										
Gloss 75°-Top	%	±5	45										
IGT - Top	m/s	≥	1.2										
Cobb 60s	g/m ²	±15	40										
Ply Bond	J/m ²	≥	130										
Squareness	mm	≤	2.0										
Size Deviation	mm	≤	2.0										

★ Non regular substance, minimum qty 800 t / substance for production